

TECHNICAL SPECIFICATION:

ROLL DIMENSIONS:

LENGTH	WIDTH	AREA	THICKNESS	WEIGHT g/m ²	DENSITY kg/m ³
10m	1.5m	15m	7mm	650g/m ²	93kg/m ³

TESTING DATA:

STANDARD	DESCRIPTION	SPRINGBOND 7mm
BS 4790	Flammability	Pass – Low Radius
BS 14499: 2015	Underlays & Textile Floor Coverings	H/CU Heavy Contract Use
ISO 13934-1	Breaking Strength & Elongation	Elongation at 30N – 1.13% Breaking Strength 166N
ISO 3416:1986 (2012)	Static Loading	Thickness Loss After 24 hrs Recovery 24.3%
ISO 2094:1999	Dynamic Loading Test	Thickness Loss After 1000 Impacts 22.5%
BS 4098:1975 (2003)	Work Of Compression Test	Mean Work Of Compression Retained 57.8%
BS 14499 Appendix A:2015(2015)	Resistance to Breaking & Cracking – Degree of Cracking	None
BS 4745	Thermal Insulation	2 Tog
BS 1902-5.8(1992)	Thermal Conductivity	0.0344 W/M2K
ISO140	Impact Sound Reduction	37db
Sustainability	Fully recyclable at end of serviceable life	YES

USAGE:

	COMFORT	DURABILITY	AREA RECOMMENDATIONS (★ – HIGHLY RECOMMENDED)			
			BEDROOMS	LIVING ROOMS	HALL, LANDINGS, STAIRS, CORRIDORS	HEAVY FLOOR, WHEEL TRAFFIC & CASTOR CHAIRS
7mm	7/10	9 /10	★	★	★	★

INSTALLATION:

Subfloors should be dry, clean and free of oil, grease & damp. **STRETCH FIT** suitability

Fitting should meet the British Standard code of practise BS5325 & be undertaken by experienced fitters.



BRITISH MADE



FLAME RESISTANT



COMFORT & SUPPORT



NOISE REDUCING



CHEMICAL FREE



EASY FIT



ECO-FRIENDLY



THERMAL INSULATION



SAFE – NO HARMFUL VOCs



BREATHABLE



85% RECYCLED CONTENT



100% RECYCLABLE



OF WHICH 30% IS TWICE
RECYCLED



Texfelt
Underlay & Fibre Technology

Unit 2, Cutler Heights Business Park,
Cutler Heights Lane, Bradford, BD4 9AW, UK.
T: +44 (0) 1274 905411 **E:** info@texfelt.co.uk
W: www.texfelt.co.uk

ECO ENGINEERED IN THE UK BY TEXFELT LTD



KYTECH
AIR LAY